


TESORO

BOHEMIA COLLECTION

| | | | |
|---|--|--|-----------------------------------|
| CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR | Tufting 1/4" loop pile Tufté 1/4" loop pile Getuftet 1/4" loop pile Getuft 1/4" loop pile | FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID | EN ISO 105-B02 ≥ 5-6 |
| PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL | 100% PP | COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID | EN ISO 105-E01 ≥ 4-5 |
| SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG | Texflor® back | FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG | EN 13501-1 E _{FL} -s1 |
| PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT | ± 660 gr/m ² | WIDTH LARGEUR BREITE BREEDTE | EN ISO 3018 ca. 400 cm |
| TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT | ± 1.850 gr/m ² | DESIGN REPEAT CM RACCORD CM RAPPORT CM DESSINRAPPORT CM | 10,5 (W) x 10,7 (H) |
| PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE | ± 5 mm | | |
| TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE | ± 8 mm | | |
| TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN | ± 60.000/m ² | | |
| PRODIS / GUT | 6BEDFEE5 | | |
| CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE | EN 1307 22 - LC2 |  | |

balta

EAC



BALTA INDUSTRIES
Wakkensteenweg 2, B-8710 Sint-Baafs-Vijve
balta-carpets.com

| |
|---|
| EN 14041  |
| 21 |
| BALTA INDUSTRIES Wakkenstwg 2 - BE 8710 Sint-Baafs-Vijve |
| DOP: 1010#BA0AEL |
| Textile Floor Covering EN 1307 |
|  |
| www.baltamediabank.com |