


SPRY

RITZY COLLECTION PROVISIONALLY

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" loop pile print Tufté 1/10" loop pile print Getuftet 1/10" loop pile print Getuft 1/10" loop pile print	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PA	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Ultratex® back	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 E _{FL} -s1
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 255 gr/m ²	WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 1.250 gr/m ²	DESIGN REPEAT CM RACCORD CM RAPPORT CM DESSINRAPPORT CM	95 (W) x 92,4 (H)
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 4 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 6,5 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 170.000/m ²		
PRODIS / GUT			
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC1		



BALTA INDUSTRIES
Wakkensteenweg 2, B-8710 Sint-Baafs-Vijve
balta-carpets.com

EN 14041 
21
BALTA INDUSTRIES Kanegemstraat 15 - BE 8700 Tielt
DOP: 1011#IE00EL
Textile Floor Covering EN1307

www.baltamediabank.com