


INSPIRE



Emissions tested in accordance with DIBt-principles

Product Information

Usage classification	EN ISO 10874 EN 685		22
Wear layer	EN ISO 24340 EN 429		0,20 mm
Total thickness	EN ISO 24346 EN 428		2,80 mm
Total weight	EN ISO 23997 EN 430		1500 gr/m2
Standard widths	EN ISO 24341 EN 426		2 - 3 - 4m
Standard length	EN ISO 24341 EN 426		30m

Technical Information

Light stability	EN ISO 105 B02		≥ 6
Dimensional Stability	EN ISO 23999 EN 434		≤ 0,40 %
Underfloor heating	EN 12667		Suitable
Residual Indentation	EN ISO 24343-2 EN 433		≤ 0,35 mm
Reaction to fire	EN 13501-1		Bfl/S1
Slip resistance	DIN 51130		R10
Dynamic coefficient of friction	EN 13893		> 0,6