

TECHNICAL DATA FOR MACHINE WOVEN RUGS

		DECLARED VALUES	
Features	Units	Value	TEST METHOD
Product trade name		ADRIA	Defined by Sintelon
Quality type		Face to face, 1/2-V	ISO 2424
No. of chores	ch	2	
Weave density	on 10cm	32/32	ISO 1763
No. of points	per sqm		ISO 1763
No. of knots	per sqm	102.400	ISO 1763
Pile height	mm		ISO 2549
Tolerance allowed in pile height	%		Defined by Sintelon
Total thickness	mm	4	ISO 1765
Tolerance allowed in total thickness	%	- 7	Defined by Sintelon
Raw material composition:	%		
Pile	%	100%PP-BCF (1% UV stabilizer)	ISO 1833
Chain Warp	%	PES	ISO 1833
Stuffer	%	PES cotton	ISO 1833
Weft	%	PP tape	ISO 1833
Binder for backing	%	Latex	Defined by Sintelon
Mass:	g/sqm		
Pile	g/sqm	660	ISO 8543
Chain Warp	g/sqm	70	ISO 8543
Stuffer	g/sqm	55	ISO 8543
Weft	g/sqm	370	ISO 8543
Binder for backing	g/sqm	95	Defined by Sintelon
Total mass:	g/sqm	1250	ISO 8543
Tolerance allowed in mass:	%	- 7	Defined by Sintelon
<p>Note:</p> <p>Tolerance in defined rug size:</p> <ul style="list-style-type: none"> + -3 % for carpet widths and lengths by 100 cm; + -2 % for carpet widths and lengths over 100 cm. <p>Tolerance in pile height, thickness and carpet mass in plus is not limited.</p>		<p>Tolerance in defined runner size:</p> <ul style="list-style-type: none"> + -3 % for runners width by 100cm; + -2 % for runners width over 100cm. Length of the runner roll: min 15 m Tolerance allowed in the length of the runner roll: 0.2 %. 	