

▼ Properties



▼ Product information

|                     | Norm          | Symbol |                       |
|---------------------|---------------|--------|-----------------------|
| Classification      | EN 685-ASTM23 |        | 22                    |
| Thickness Wearlayer | EN 429        |        | 0.20 mm               |
| Total Thickness     | EN 428        |        | 2.40 mm               |
| Total Weight        | EN 430        |        | 1350 g/m <sup>2</sup> |
| Standard Length     | EN 426        |        | 30 m                  |

▼ Technical information

|                       | Norm        | Symbol |              |
|-----------------------|-------------|--------|--------------|
| Interlayer            |             |        | GV           |
| Light Stability       | ISO 105-B02 |        | ≥ 6          |
| Dimensional Stability | EN 434      |        | ≤ 0.40%      |
| Underfloor Heating    | EN 12667    |        | Suitable     |
| Residual Indentation  | EN 433      |        | ≤ 0,35 mm    |
| Castor Chair          | EN 425      |        | Not Suitable |
| Reaction to Fire      | EN 13501-1  |        | Bfl S1       |
| Slip Resistance       | DIN 51130   |        | R10          |